

Characteristic (TPC)	TPC 1x
Dirt content on 44u aperture, max %wt	0.015
Ash content, max %wt	0.14
Nitrogen, max % wt	0.40
Volatile matter, max %wt	0.29
Wallace rapid plasticity (Po), min	38
Plasticity retention index (PRI), min %	79

This grade falls under the VGR category (Visually Graded Rubber) for which there are no standard specifications. The values given above are only for reference purposes.