



Characteristic Skim Block	Sample A	Sample B	Sample C	Sample D
Dirt content on 44u aperture (max %wt)	0.038	0.01	0.005	0.005
Ash content (max %wt)	0.38	1.32	1.06	1.52
Nitrogen (max % wt)	2.35	0.54	0.38	0.32
Volatile matter (max %wt)	1.39	0.52	1.80	1.76
Wallace rapid plasticity (Po) min	47	50	30.5	28
Plasticity retention index (PRI) min %	40.4	45	32.8	14.3
Mooney Viscosity ML(1'+4') 100 C	93.7	86.0	71.3	91.9

Copyright Oriental Rubber Products Co., Ltd , All right Reserved. Please visit www.orientalrubberproducts.com for more information