

Characteristic (TSR 10CV)	Thailand (STR 10CV)	Indonesia (SIR 10VK)	Vietnam (SVR 10CV)	Malaysia (SMR 10CV)
Dirt content on 44u aperture, max %wt	0.08	0.10	0.08	0.08
Ash content, max %wt	0.60	0.75	0.60	0.75
Nitrogen, max % wt	0.60	0.6	0.60	0.60
Volatile matter, max %wt	0.80	0.8	0.80	0.80
Wallace rapid plasticity (Po), min	-	30	-	-
Plasticity retention index (PRI), min %	50	60	50	50
Mooney Viscosity ML(1'+4') 100 C	60+7/-5	60+/-5	60+7/-5	60+7/-5