

Characteristic (TSR 10)	Thailand (STR 10)	Indonesia (SIR 10)	Vietnam (SVR 10)	Malaysia (SMR 10)
Dirt content on 44u aperture, max %wt	0.08	0.10	0.08	0.08
Ash content, max %wt	0.60	0.75	0.60	0.75
Nitrogen, max % wt	0.60	0.60	0.60	0.60
Volatile matter, max %wt	0.80	0.80	0.80	0.80
Wallace rapid plasticity (Po), min	30	30	30	30
Plasticity retention index (PRI), min %	50	60	50	50