

Characteristic (TSR 20)	Thailand (STR 20)	Indonesia (SIR 20)	Vietnam (SVR 20)	Malaysia (SMR 20)
Dirt content on 44u aperture, max %wt	0.16	0.20	0.16	0.16
Ash content, max %wt	0.80	1.00	0.80	1.00
Nitrogen, max % wt	0.60	0.60	0.60	0.60
Volatile matter, max %wt	0.80	0.80	0.80	0.80
Wallace rapid plasticity (Po), min	30	30	30	30
Plasticity retention index (PRI), min %	40	50	40	40