

Characteristic (ADS XL)	ADS XL
Dirt content on 44u aperture, max %wt	0.032
Ash content, max %wt	0.19
Nitrogen, max % wt	0.32
Volatile matter, max %wt	0.57
Wallace rapid plasticity (Po), min	55
Plasticity retention index (PRI), min %	78.2
Mooney Viscosity ML(1'+4') 100 C	91.9

*This grade falls under the VGR category (Visually Graded Rubber) for which there are no standard specifications. The values given above are only for reference purposes.*