

Characteristic (TSR 5)	Thailand (STR 5)	Indonesia (SIR 5)	Vietnam (SVR 5)	Malaysia (SMR 5)
Dirt content on 44u aperture, max %wt	0.04	0.05	0.05	0.05
Ash content, max %wt	0.60	0.50	0.60	0.60
Nitrogen, max % wt	0.60	0.60	0.60	0.60
Volatile matter, max %wt	0.80	0.80	0.80	0.80
Wallace rapid plasticity (Po), min	30	30	30	30
Plasticity retention index (PRI), min %	60	70	60	60