



Characteristic (TSR CV50)	Indonesia (SIR 3CV50)	Vietnam (SVR CV50)	Malaysia (SMR CV50)
Dirt content on 44u aperture, max %wt	0.03	0.02	0.02
Ash content, max %wt	0.50	0.40	0.50
Nitrogen, max % wt	0.60	0.60	0.60
Volatile matter, max %wt	0.60	0.80	0.80
Wallace rapid plasticity (Po), min	30	-	-
Plasticity retention index (PRI), min %	60	60	60
Mooney Viscosity ML(1'+4') 100 C	50+/-5	50+/-5	50+5/-5